

(19) World Intellectual Property
Organization
International Bureau




(43) International Publication Date
11 August 2005 (11.08.2005)

PCT

(10) International Publication Number
WO 2005/073442 A1

- (51) International Patent Classification⁷: **D01F 9/00**
- (21) International Application Number:
PCT/KR2004/000188
- (22) International Filing Date: 2 February 2004 (02.02.2004)
- (25) Filing Language: Korean
- (26) Publication Language: English
- (71) Applicant (for all designated States except US): **RAISIO CHEMICALS KOREA INC.** [KR/KR]; 178-1, Hwakyee-ri, Dong-myeon, Cheonan-si, Chungcheongnam-do 330-090 (KR).
- (72) Inventor: **KIM, Hak-Yong** [KR/KR]; 410-6, Pyunghwadong 2ga, Wansan-gu, Jeonju-si, Chonrabuk-do 560-865 (KR).
- (74) Agent: **CHO, Hwal-Rai**; Suite 1507, Yoksam Heights Bldg, 642-19, Yoksam-dong, Kangnam-gu, Seoul 135-981 (KR).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A PROCESS OF PREPARING CONTINUOUS FILAMENT COMPOSED OF NANOFIBERS



(57) Abstract: Conventional electrospinning was problematic in that it is incapable of making a continuous filament (yarn) by a simple and continuous process. To solve the above problem, there is provided a method for making a continuous filament consisting of nanofibers according to the present invention, wherein a polymer spinning liquid is electrostatically spun to a collector 7 through nozzles 5 to obtain a nanofiber web 17a of ribbon form, then the nanofiber web 17a is passed through an air twister 18 and twisted to obtain a nanofiber filament 17b of a continuous filament form, and then the nanofiber filament 17b is drawn.